

Tripoxy™

Two Component, Polyamide Cure, Epoxy Enamel

SELECTION DATA

DESCRIPTION:

Tripoxy 41 series is a two component (1:1 mix ratio), high solids, solvent borne, polyamide cure, high gloss, epoxy enamel with USDA approval for incidental food contact. The cured film is extremely dense and very hard without being brittle. It is impermeable and insensitive to water and is suitable for submersion service. It has excellent resistance to common solvents, all alkalis and excellent splash and spill resistance to most acids. **41** series has excellent adhesion but just adequate wetting and penetration. Like all epoxies **Tripoxy** chalks heavily with exposure to sunlight; noticeable at 6 months and complete in 12–18 months. **Tripoxy** is also available as a clear; see Data Sheet 41G900.

USES:

Tripoxy is recommended for the plant maintenance of machinery, structural steel, catwalks, rails, lining of storage tanks, metal doors, walls and floors. It is also used as an abrasion and chemical resistant floor finish for industrial concrete floors, warehouses, fire stations, garages, even residential showers. **41** series is also recommended to protect wood in constantly damp environments and as a "tile like glaze coat" for heavy wear commercial/institutional walls and doors. Such uses include jail cells, hospital walls, school corridors, gyms, public rest rooms, commercial kitchens, etc. Other uses included surfaces in meat and poultry processing plants, sulfur fume problem areas in geothermal plants, and fertilizer handling equipment. It has even been used on the lining of oyster larvae storage tanks.

ADVANTAGES:

- Superior performance + competitive price.
- Resists many common acids, alkalis, chemicals solvents, gasoline, fumes and many harsh chemicals. USDA approved.
- No hazards in dry state.

LIMITATIONS:

- Read Chemical Resistance Guide before using in areas subject to regular direct chemical contact.
- On grade concrete must have sheet type moisture barrier. If moisture can get into the slab from below any impermeable coating will fail.
- White exhibits moderate yellowing.
- Limited color selection.

PHYSICAL PROPERTIES

VOC: [catalyzed @ unreduced]....394 g/l – (3.3 #/gal.)
[Also classed as an architectural Tile Like Glaze Coat.]

APPEARANCE: [Gloss at 60°]

High Gloss (G) [use 41B] 85 – 92
Semigloss (S) [use 941B] 45 – 60

WEIGHT PER GALLON: [catalyzed] 12.4 lbs.

FLASH POINT: [setaflash][mixed] 45° F.
Part A [color] 81° F.
Part B [hardener] 45° F.

PACKAGE VISCOSITY: [catalyzed] 80 – 85 KU

SOLIDS: [catalyzed]

BY Weight 73 ± 1%
BY Volume 54 ± 1%

COVERAGE: [catalyzed]

Theoretical at 1 mil DFT 869 sq.ft./gal.
Theoretical at 1.5 mils DFT 579 sq.ft./gal.
Minimum DFT 2 mils
Recommended DFT 2 – 4 mils

DRY SCHEDULE: [at 50% RH and 2 mils DFT]

	45° F.	60° F.	75° F.	90° F.
Tack free	8 hrs.	4 hrs.	2 hrs.	1½ hrs.
Rainproof	24 hrs.	12 hrs.	6 hrs.	4 hrs.
Light use	48 hrs.	24 hrs.	12 hrs.	8 hrs.
Full cure*	20 days	10 days	6 days	4 days

* Recommended prior to driving on.

COLOR AVAILABILITY:

Tripoxy is stocked in white, black and a typical industrial gray (ANSI 61). White **41** series can be tinted to pastel colors using Colortrend 844 Industrial Colorants. Clear **Tripoxy** does not accept colorants. Any non metallic color can be made with a 25 gallon minimum order.

ORDER CODE: 41 + gloss + color #
Individual products are identified by the product series number, followed by a gloss identifier (G=gloss, S=semigloss) and ending in the color number. For example, 41G633 is **Tripoxy** (41) gloss (G) Lt. Gray ANSI 70 (633). Use 941B hardener if semigloss finish is desired.

PACKAGING:

Four ea. 1 gallon cans per case 56 lbs.
Two ea. 5 gallon metal pails 132 lbs.
[2 containers per kit – color container and hardener container.]

TRIANGLE COATINGS, INC.

Tel: 510-895-8000
800-895-8000
Fax: 510-895-8800

www.tricoat.com

TRIANGLE™



Tripoxy™

Two Component, Polyamide Cure, Epoxy Enamel

APPLICATION DATA

REQUIREMENTS FOR APPLICATION:

- Proper curing occurs only above 50° F.
- Surfaces must be completely dry and applied **Tripoxy** must be protected from all forms of moisture until "rainproof" as per preceding chart.
- **41** series will lift alkyd enamels and primers and may soften/wrinkle latex enamels. Test a painted surface for compatibility before painting.
- New iron and steel should be abrasive blasted to SSPC-SP6 and must be blasted to SSPC-SP10 for submersion.
- **Tripoxy** can be applied over itself or similar epoxies if the existing paint is abraded to dull. However for chemical environment or submersion service, SSPC-SP10 is required.
- Concrete floors require special treatment, reference Tech. Advisory # 4 for complete review.
- Fumes are flammable; extinguish all pilot lights and open flames.

PRIMING:

Tripoxy is self priming on metal, wood and concrete but requires clean, profiled, rust free metal. Significant reduction is required for proper penetration into wood and concrete. On iron and steel, epoxy primers with corrosion inhibiting pigmentation can be used for additional protection. Primers are used on sheetrock, plaster and CMU to provide a uniform gloss. On non ferrous metal and iron/steel that cannot be abrasive blasted, the use of 994P PreEtch is recommended.

FILM DEVELOPMENT & THICKNESS:

Tripoxy develops its full hardness and chemical resistance at 3 mils. Heavier films attempted in one coat may cause pinhole voids. Use 2 coats on profiled iron and steel. **Tripoxy** repaints over itself in on coat. Drywall and CMU will vary significantly as to texture/profile. In shower rooms or similar constantly wet environments, 2 coats to produce a 4 mils DFT are recommended. In dry areas such as school corridors or jail cells, one coat to produce a 2 – 3 mils DFT is appropriate. Spread rates can vary from 200 – 400 sq.ft./gal. per coat.

MIXING:

Catalyzing: Mix ratio is 1:1 by volume. Pour Part B into a third container. Stir Part B while adding Part A until homogenous.

Induction Time: 30 min. After being catalyzed,

Tripoxy must stand without being agitated or used for 30 minutes. Only after induction time may **Tripoxy** be thinned if necessary. Discontinue use if mixture starts to gel.

Pot Life	50°	65°	80°	95°
Time @ :	12 hrs.	8 hrs.	6 hrs.	3 hrs.

THINNING:

Tripoxy cannot be thinned with solvents in VOC regulated areas. In unregulated areas use up to 5 to 10% of AT65 Thinner.

APPLICATION:

Steel and wood are brushed or sprayed. Masonry and drywall walls and concrete floors are typically rolled. Rolling will introduce bubbles and when protection from water or chemicals is required, two or more coats are mandatory when rolling.

Brush: Any professional quality.

Rolling: ¼" mohair for smooth surfaces and ½" lambswool for CMU and/or textured walls.

Conventional Spray: At package viscosity, pressure feed only. Binks 18 or 2001 gun, .055 fluid nozzle @ 15 – 25 psi fluid and 80 – 90 psi air pressure.

HVLP: Binks BBR with a 94 nozzle or equivalent.

Airless: ¾ – 1 gpm; 20:1 + ratio pumps capable of sustaining +2000 psi with .019" – .021" tips.

CLEANUP: AT17 Wash Thinner
Rinse clear with clean AT65 Epoxy Thinner or Xylene

SAFETY AND HANDLING

FLASH POINT: [Part A] 81° F. (28° C.)

FLASH POINT: [Part B] 45° F. (07° C.)

SHIPPING DESCRIPTION: [CFR 49]

Ground/Air/Vessel: Paint, 3, UN1263, PG II
Required Label: FLAMMABLE LIQUID
Required Marking: PAINT UN1263

IMDG PACKAGING:

FLAMMABLE LIQUID, class 3.2, UN1263, II

IMDG STOWAGE: Category B

UNIFORM FIRE CODE: [CFR 29] CLASS I-B

STORAGE TEMPERATURE: 120° F. max.

SHELF LIFE: [warranted] 1 Year

"HMIS" RATINGS: H - 2; F - 3; R - 0; PP - H

(11/16/01)

WARRANTY: The statements made herein, on labels, product bulletins, or by any of Triangle Coatings', Inc. employees or agents concerning this product are given for general information only. Due to variables beyond Triangle's control in application, surface preparation, surface temperature, humidity and other variable factors Triangle assumes no liability for any claim that may arise out of the use of its products and disclaims any warranty expressed or implied relating to the storage, application, thinning, merchantability, Buyer's assumption of performance, and the fitness for a particular purpose. Receipt of products from Triangle or its agents constitutes acceptance of the terms of this warranty. In the event that Triangle finds that the product delivered is not of Triangle's standard quality, Triangle will at its sole discretion, either replace the product or refund the purchase price. Triangle's choice of one of these remedies shall be the Buyer's sole remedy. Triangle will under no circumstances be liable for consequential damages, except insofar as liability is mandated by law. Triangle will deliver products at agreed times insofar as it is reasonably able to do so, but it will not be liable for failure to deliver on time when the failure is beyond its reasonable control.