TRIANGLE INDUSTRIAL TriKote STM

Product Finishing Topcoat

Specifications

DESCRIPTION:

TriKote S is a fast air dry, high gloss coating designed for spray applications. This topcoat exhibits very good adhesion to properly prepared ferrous metals. **TriKote S** provides a hard scratch resistant finish that has moderate gloss and color retention on exterior exposure.

USE:

TriKote S is primarily used by job shops and metal part manufacturers when a cost effective coating is required. This product is an excellent choice for steel shelving, trash containers, gas cylinders, and other miscellaneous metal parts.

ADVANTAGES:

- Very high gloss
- Extremely smooth surface
- Direct to metal adhesion (ferrous substrates)
- Fast dry
- Cost effective

LIMITATIONS:

- Formulated for spray application
- Not recommended for submersion below grade, or direct chemical contact service
- Requires corrosion resistant primer for long term salt spray resistance

Properties

VOC: [as packaged] 250 g/l – (2.1 lbs/gal)
FLASH POINT: [setaflash]<73° F
APPEARANCE:
Gloss (G) @ 60°85-90+
WEIGHT PER GALLON: [average] 11.0 lbs
PACKAGE VISCOSITY: [#3 Zahn] 25-30 sec
SOLIDS: [average]
By Weight69 ± 10%
By Volume54 ± 10%
COVERAGE: [average]
Theoretical at 1.5 mils DFT 584 sq ft/gal
Required Minimum DFT 1.5 mils
DRY SCHEDULE: [at 50% RH and 1.5 mils DFT]

 45° F
 60° F
 75° F
 90° F

 Dry to Touch
 2 hrs
 1 hrs
 30 mins
 15 mins

 Handle/Recoat
 5 hrs
 2 hrs
 1 hrs
 45 mins

Full Cure 7 days 7 days 7 days 5 days
After 1 week, light sanding may be necessary if cured coating is subject to exterior exposure for extended periods.

COLOR AVAILABILITY:

TriKote S is available in factory stock colors. Triangle stocks safety and traditional implement colors. Many colors may be tinted, however, special costing will be applied.

G = gloss

S = semi-gloss

M = matte

F = flat

PACKAGING:

Four 1 gallon cans per case

5 gallon pails

55 gallon drums

250 gallon totes





TriKote S[™] Product Finishing Topcoat

Application Data

SURFACE PREPARATION:

- Surfaces to be coated must be clean, dry, and free of oil, grease, dust, flaky rust, mill scale, and other foreign matter that could interfere with adhesion.
- Recommended surface preparation includes iron phosphate, zinc phosphate, and surface blasting that removes all mill scale.
- · Wood and galvanized metal must be primed

RECOMMENDED PRIMERS:

- 954P ShopCoat S
- 955P TriPrime S
- 956P TriBond S

Consult your Triangle Coatings representative for water based primer recommendations.

APPLICATION:

Apply **TriKote S** using HVLP, air-assisted airless, or airless.

HVLP:

Air Assist Airless:

Fluid Tip:	013015"
Fluid pressure:	
Air Cap Pressure:	10 psi

Airless:

Fluid Tip:	013015"
Fluid Pressure:	2 000 - 2 500 psi

THINNING:none

CLEANUP: solvent

Health & Safety

WARNING:

FLAMMABLE LIQUIDAND VAPOR. May be harmful if swallowed or inhaled. Vapor may affect the brain or nervous system causing dizziness, headache or nausea and can cause nose and throat irritation. Keep away from sparks, heat or open flame. Use with adequate ventilation. Avoid breathing of vapor. Avoid contact with eyes, skin, and clothing. Wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application unless air monitoring demonstrates vapor levels are below applicable limits. Follow respirator manufacturer's directions for use. Keep container closed when not in use. If spillage occurs, absorb and dispose of according to local regulations.

NOTICE:

Intentional misuse by deliberately concentrating and inhaling contents may be harmful or fatal. Reports have associated repeated and prolonged occupational overexposure to solvents with permanent brain and nervous system damage.

FIRST AID:

Should eye contact occur, flush with plenty of water for at least 15 minutes and get medical attention if vision is disturbed. For skin, wash thoroughly with soap and water. If swallowed, seek medical attention immediately. DO NOT induce vomiting.

THIS PRODUCT IS FOR PROFESSIONAL USE ONLY.

KEEP THIS PRODUCT OUT OF THE REACH OF CHILDREN.

Shipping & Handling

HMIS RATINGS: H - 2; F - 3; R - 0; PP - H

WARRANTY: The statements made herein, on labels, product bulletins, or by any of Triangle Coatings', Inc. employees or agents concerning this product are given for general information only. Due to variables beyond Triangle's control in application, surface preparation, surface temperature, humidity and other variable factors Triangle assumes no liability for any claim that may arrise out of the use of its products and disclaims any warranty expressed or implied relating to the storage, application, thinning, merchantability, Buyer's assumption of performance, and the fitness for a particular purpose. Receipt of products from Triangle or its agents constitutes acceptance of the terms of this warranty. In the event that Triangle finds that the product delivered is not of Triangle's standard quality, Triangle will at its sole discretion, either replace the product or refund the purchase price. Triangle's choice of one of these remedies shall be the Buyer's sole remedy. Triangle will under no circumstances be liable for consequential damages, except insofar as liability is mandated by law. Triangle will deliver products at agreed times insofar as it is reasonably able to do so, but it will not be liable for failure to deliver on time when the failure is beyond its reasonable control.